






II	REZULTATI ISPITIVANJA:	Elementi kvaliteta		Odstupanje (%)	
		deklarisano	ustanovljeno	dozvoljeno	ustanovljeno
				F.C0.011	
1.	Širina (cm):		/	-1,2	
2.	Masa po jedinici površine (g/m ²):		280,3	-5	
3.	Debljina				
4.	Sirovinski sastav (%):				
	<u>LICE POLIESTAR</u>		100	± 2	Ø
	<u>NALIČJE POLIESTAR</u>		100	± 2	Ø
5.	Prekidna sila (N):				
	- u pravcu osnove		1804	-5	
	- u pravcu potke		1262	-5	
6.	Prekidno izduženje (%):				
	- u pravcu osnove		38,9	-2	
	- u pravcu potke		30,7	-2	
7.	Gustina žica (ž/10 cm)				
	- po osnovi				
	- po potki				
8.	Skupljanje pri pranju na 40 ⁰ C %				
	- po dužini		Ø		
	- po širini		Ø		
9.	Međusobna upravnost žica mm		1		
9.	Postojanost obojenja na: promena / prelaz na:			POLIESTAR / PAMUK	
	a) pranje na 40 ⁰ C			4/4/4	
	b) znoj (alkalni+kiseli)			4/4/4	
	c) otiranje - suvo			4	
	d) otiranje - mokro			4	
	e) peglanje na 110 ⁰ C			4/4	
	f) hemijsko čišćenje			4/4/4	
	g) voda			4/4/4	
10.	Način održavanja				
	a) pranje			Prati na temperaturi do 40 ⁰ C	
	b) peglanje			Peglati na temperaturi do 110 ⁰ C	
	c) hemijsko čišćenje			Dozvoljeno hemijsko čišćenje perhoretienom	
	d) sušenje			Ocediti, obesiti i sušiti	
	e) beljenje			Zabranjeno beljenje	

